

CONCRETE PRIMER

Acrylic

- **Fast Dry Time**
- **Improves Adhesion**
- **Adds Strength**

FEATURES AND BENEFITS

- One to two hour dry time, allows for same day installation of flooring
- Improves adhesion to gypsum-based leveling compounds
- Helps bond new concrete to old concrete, masonry and similar materials

Titebond® Concrete Primer is used over Gyp-Crete and lightweight concrete to provide a bondable surface for the installation of hardwood floors. It also performs exceptionally well as an additive to cement based patching and leveling compounds used over uneven or damaged subfloors. It promotes adhesion of these compounds to concrete, wood, tile and other sound floor coverings. When added to Portland cement and a sand mixture, Titebond Concrete Primer enhances the bonding of new, wet stucco or concrete to old concrete, masonry, stucco and similar surfaces. It provides a highly water-resistant and resilient base.

ORDERING INFORMATION

- Gallon Jug: Units Per Case: 2
Cases Per Pallet: 63
Weight: 18.27 lbs.
Product Code: 15136



**FAST
DRY
TIME**

**IMPROVES
ADHESION**

**ADDS
STRENGTH**

Titebond®
THE PRO'S ADVANTAGE™

PHYSICAL PROPERTIES

TYPE: Modified acrylic

STATE: Liquid

SOLIDS: 28%

FLASHPOINT: >200°F (Pensky-Martens Closed Cup)

STORAGE LIFE: 24 months in tightly closed container

pH: 9.5

WEIGHT/GALLON: 8.6 lbs.

VISCOSITY: Very thin liquid

SUBFLOOR PREPARATION

Remove dust, dirt, oil, grease and any other foreign material before applying Titebond Concrete Primer.

INSTRUCTIONS

In order to properly glue down wood flooring to Gyp-Crete or lightweight concrete, the surface must be primed with Titebond Concrete Primer. For this application, the Primer must be applied at a rate of 400 square feet per gallon using a mix of one-part clean water and two part Primer. Apply evenly with a squeegee, brush, roller or spray. Allow 45 minutes or more before applying a second coat. Allow to dry 1-2 hours before applying adhesive over the primer/sealer.

PATCHING COMPOUND

Be certain surfaces are clean, and free from dust, dirt and loose materials. Using water only, dampen entire surface to be patched. Use proper dry patching mix of concrete, plaster, cement or stucco and two parts of the Concrete Primer to one part water. For outstanding adhesion use straight Concrete Primer as the liquid portion.

FLOOR – LEVELING COMPOUND

Repair uneven subfloors of concrete. It will level spalled concrete, offsets and cracks in wood and concrete floors and generally provide a sound and solid base for the installation of finished flooring. For Portland cement mixes, approximately 2-1/2 gallons per 94 lb. bag. Use proper dry concrete mix. For ready-mixes, use approximately 2-1/2 pints per 50 lb. bag. Additional Concrete Primer may be added for superior strength. Add Primer without dilution, in above proportions, then add water to the desired consistency.

LIMITATIONS

Titebond Concrete Primer is formulated specifically for use with various Franklin International flooring adhesives. While it will perform satisfactorily with other adhesives, it can be hardened or softened by the solvents in some adhesives. If there is any question about the adhesive being used in conjunction with Titebond Concrete Primer, consult Franklin International Technical Service at 1-800-347-4583 or perform the following test: Apply a small amount of concrete mixture to the surface and allow it to dry at least 3-5 days. Bond an assembly with the adhesive you intend to use and allow to set for 72 hours. Separate the assembly and inspect the glue line. If the bond is strong and the adhesive is firm, you should have no problems.

IMPORTANT NOTICE: Our recommendations, if any, for the use of this product are based on tests believed to be reliable. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing laws and/or patents covering any material or use.

WARRANTY: The full warranty for Titebond Primer and all Titebond flooring products can be obtained at www.Titebond.com or by calling 1.800.347.4583.

**FAST
DRY
TIME**

**IMPROVES
ADHESION**

**ADDS
STRENGTH**

VISIT WWW.TITEBOND.COM FOR THE
MOST UP-TO-DATE PRODUCT INFORMATION



Franklin International

Columbus, Ohio 43207

614.443.0241

(Technical Service 1.800.347.4583)

© 2019 00409-3631LN FF1027